

Screen Printing Inks



# TEXYLON STICK

Code A31159865001

## PRODUCT DESCRIPTION

Solvent based polyurethanic adhesive

## APPLICATION FIELDS

Adhesive for the realization of solvent based transfers.

## APPLICATION PROCESS

<b>Substrates</b>	100% cotton, cotton mixed with synthetic fibers, elastic substrates. Substrates may be white or coloured.
<b>Th/cm</b>	32 to 55
<b>Emulsion</b>	<ul style="list-style-type: none"> <li>ZERO - IN SV PLUS VIOLA</li> <li>ZERO - IN SR-V</li> </ul>
<b>Squeegee</b>	Square edge Squeegee hardness 60 - 65 Shores
<b>Transfer</b>	100 - 110°C during 90 seconds
<b>Thinner</b>	<b>DILUENTE 90.924</b> <b>DILUENTE 90.918 LENTO</b>
<b>Cleaning</b>	<b>SOLVENTE LAVAGGIO LQ 90.920</b>
<b>Storage</b>	If kept in its original sealed package, the product has a shelf-life of 2 years
<b>Package</b>	1 Kg
<b>Safety Data Sheet</b>	Available upon request

## PREPARATION

Before using it, the ink must be mixed well and, in case, diluted, according to printing requirements.

## TECHNICAL FEATURES

The performance of the product, printed with a 43 Th/cm screen, is 18-20 m<sup>2</sup>/Kg. These data are merely an indication, since they depend on the dilution, the substrate and the printing equipment.

## GENERAL FEATURES

- Good elasticity
- After transferring, the prints resist water washing at 40°C.

## SPECIAL INSTRUCTIONS

- Always test the characteristics of the product, before starting production.
- The above information is the result of previous knowledge and experience; it is neither a guarantee nor an assurance.
- This adhesive does not resist dry clearing and bleaching.

## IMPORTANT NOTE

The information given in this technical sheet is not intended to be exhaustive and any person, using the product for any purpose other than that specifically recommended in this sheet without first obtaining written confirmation from us to the suitability of the product for the intended purpose, does so at his own risk.

While we endeavour to ensure that all advice we give about the product is correct, we have no control over either the quality or condition of the substrate or the many factors affecting the use and application of the product.

Therefore, unless we specifically agree in writing to do so, we do not accept any liability whatsoever or howsoever arising for the performance of the product or for any loss or damage arising out of the use of the product.

The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.